

PU 95 A red smooth, reinforced aramid

Order No.	Diameter ∅		Cross section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley ∅		approx. Working Load/Belt*	
	mm	inch			m	ft	mm	inch	daN	lbs
FBRN095RM	9,5	3/8	0,710	8,5	150	500	120	4,7	35,5	78,1

* = coefficient of friction μ :1

approx. 98° Shore A

- Recommended pretension 1 - 2%
- Working tension approx. 50 daN/cm²

Coefficient of friction μ : Steel: approx. 0,35 | PE: approx. 0,15 | HDPE: approx. 0,10