



Polyester TPE 63 D beige smooth, reinforced polyester

**63° Shore D .
approx. >100° Shore A**

- Recommended pretension 1 - 2 %
- Working tension
approx. 68 daN/cm²

Order No.	Diameter ∅		Cross section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley ∅		approx. Working Load/Belt*	
	mm	inch			m	ft	mm	inch	daN	lbs
FBRT063NGA	6,3	1/4	0,310	3,8	150	500	100	3,9	21,1	47,4
FBRT095NGB	9,5	3/8	0,710	8,5	107	350	150	5,9	48,3	108,6
FBRT095NGA	9,5	3/8	0,710	8,5	150	500	150	5,9	48,3	108,6
FBRT125NGA	12,5	1/2	1,230	14,8	150	500	200	7,8	83,6	187,9

* = coefficient of friction μ :1

Coefficient of friction μ : Steel: approx. 0,35 | PE: approx. 0,15 | HDPE: approx. 0,10 | **FDA/EC/BfR- conform**