

Weldable reinforcement

PU 75 A orange, reinforced glass fiber PU



Order No.	Profile dimension	Cross section	approx. Weight	Standard Roll		Recommended Min. pulley \varnothing		approx. Working Load/Belt*	
	mm	cm ²	kg/100 m	m	ft	mm	inch	daN	lbs
FBZKP75A10GL	10 x 6 (Z)	0,48	6	50	164	80	3,2	9,6	21,1
FBZKP75A13GL	13 x 8 (A)	0,82	10	50	164	100	3,9	16,4	36,9
FBZKP75A17GL	17 x 11 (B)	1,46	18	50	164	140	5,5	29,2	65,6
FBZKP75A22GL	22 x 14 (C)	2,40	29	50	164	180	7,1	★	★

approx. 80° Shore A

- Recommended pretension 1 - 2%
- Working tension approx. 22 daN/cm²

Coefficient of friction μ : Steel: approx. 0,70 | PE: approx. 0,40 | HDPE: approx. 0,35

★ = stronger carrier materials upon request

* = coefficient of friction μ :1

PATENT

DE19900551C1
US Patent No. 6,468,656