



PU 80 A orange, reinforced polyester

Order No.	Profile dimension	Cross section	approx. Weight	Standard Roll		Recommended Min. pulley \varnothing		approx. Working Load/Belt*	
	mm	cm ²	kg/100 m	m	ft	mm	inch	daN	lbs
FBJ8MOGA	8x5 (M)	0,32	4	30	100	50	2,0	9,6	21,1
FBJ10ZOGA	10x6 (Z)	0,48	6	30	100	60	2,4	14,4	31,7
FBJ13AOGA	13x8 (A)	0,82	10	30	100	90	3,5	24,6	54,1
FBJ13AOGA001	13x8 (A)	0,82	10	50	164	90	3,5	24,6	54,1
FBJ17BOGA	17x11 (B)	1,46	18	30	100	120	4,7	43,8	96,4
FBJ17B0GC	17x11 (B)	1,46	18	100	328	120	4,7	43,8	96,4
FBJ22COGA	22x14 (C)	2,40	29	30	100	160	6,3	72,0	158,4

* = coefficient of friction μ :1

approx. 84° Shore A

- Recommended pretension
1 - 2 %
- Working tension
approx. 30 daN/cm²

Coefficient of friction μ : Steel: approx. 0,65 | PE: approx. 0,35 | HDPE: approx. 0,30 | FDA/EC/BfR-conform