



PU 85 A sapphire blue smooth

Order No.	Profile dimension	Cross section	approx. Weight	Standard Roll		Recommended Min. pulley \varnothing		approx. Working Load/Belt*	
	mm	cm ²	kg/100 m	m	ft	mm	inch	daN	lbs
FBKK06MLGAAA	6 x 4 (Y)	0,19	2,3	100	328	45	1,8	3,2	7,1
FBKK08MLGAAA	8 x 5 (M)	0,32	4	100	328	50	2,0	5,4	12,0
FBKK10ZLGAAA	10 x 6 (Z)	0,48	6	50	164	70	2,8	8,2	18,1
FBKK13ALGAAA	13 x 8 (A)	0,82	10	50	164	90	3,5	13,9	30,7
FBKK17BLGAAA	17 x 11 (B)	1,46	18	50	164	120	4,7	24,8	54,6
FBKK22CLGAAA	22 x 14 (C)	2,40	29	50	164	160	6,3	40,8	89,8

approx. 88° Shore A

- Recommended pretension
6 - 8 %
- Working tension
approx. 17 daN/cm²

Coefficient of friction μ : Steel: approx. 0,60 | PE: approx. 0,30 | HDPE: approx. 0,25

FDA/EC/BfR-conform

* = coefficient of friction μ :1