



## PU 60 A transparent glatt

Artikel Nr.	Profildicke		max. Profilbreite		Gebindegröße		Empfohlener Mind.-Scheiben- $\varnothing$	
	mm	inch	mm	inch	ft	m	mm	inch
FBFF150X1TG	1,0	3/64	150	5,9	100	30	8,0	0,2
FBFF150X16TG	1,6	1/16	150	5,9	100	30	10,0	0,3
FBFF150X2TG	2,0	5/64	150	5,9	100	30	12,0	0,4
FBFF150X3TG	3,0	1/8	150	5,9	100	30	15,0	0,7
FBFF150X4TG	4,0	5/32	150	5,9	100	30	25,0	1,0

ca. 65° Shore A

- Empf. Vorspannung 1 - 2 %
- Zugspannung ca. 7 daN/cm<sup>2</sup>

Reibwerte  $\mu$ : Stahl: ca. 0,70 | PE: ca. 0,40 | HDPE: ca. 0,35 | FDA/EC/BfR-konform



## PU 65 A transparent glatt

Artikel Nr.	Profildicke		max. Profilbreite		Gebindegröße		Empfohlener Mind.-Scheiben- $\varnothing$	
	mm	inch	mm	inch	ft	m	mm	inch
FBFG150X1TG	1,0	3/64	150	5,9	100	30	8,0	0,2
FBFG150X16TG	1,6	1/16	150	5,9	100	30	10,0	0,3
FBFG150X2TG	2,0	5/64	150	5,9	100	30	15,0	0,4
FBFG150X3TG	3,0	1/8	150	5,9	100	30	20,0	0,7
FBFG150X4TG	4,0	5/32	150	5,9	100	30	25,0	1,0

ca. 72° Shore A

- Empf. Vorspannung 1 - 2 %
- Zugspannung ca. 9 daN/cm<sup>2</sup>

Reibwerte  $\mu$ : Stahl: ca. 0,70 | PE: ca. 0,40 | HDPE: ca. 0,35 | FDA/EC/BfR-konform