



PU 75 A transparent glatt


Artikel Nr.	Profildicke		max. Profilbreite		Gebindegröße		Empfohlener Mind.-Scheiben-Ø	
	mm	inch	mm	inch	ft	m	mm	inch
FBFI150X1TG	1,0	3/64	150	5,9	100	30	10,0	0,2
FBFI150X16TG	1,6	1/16	150	5,9	100	30	15,0	0,3
FBFI150X2TG	2,0	5/64	150	5,9	100	30	20,0	0,4
FBFI150X3TG	3,0	1/8	150	5,9	100	30	25,0	0,8
FBFI150X4TG	4,0	5/32	150	5,9	100	30	35,0	1,2

ca. 80° Shore A

• Empf. Vorspannung 1 - 2 %

• Zugspannung ca. 13 daN/cm²

Reibwerte μ : Stahl: ca. 0,70 | PE: ca. 0,40 | HDPE: ca. 0,35 | **FDA/EC/BfR-konform**



PU 75 A himmelblau glatt

Artikel Nr.	Profildicke		max. Profilbreite		Gebindegröße		Empfohlener Mind.-Scheiben-Ø	
	mm	inch	mm	inch	ft	m	mm	inch
FBFI100X1LG	1,0	3/64	150	5,9	100	30	10,0	0,2
FBFI150X16LG	1,6	1/16	150	5,9	100	30	15,0	0,3
FBFI150X2LG	2,0	5/64	150	5,9	100	30	20,0	0,4
FBFI150X3LG	3,0	1/8	150	5,9	100	30	25,0	0,8
FBFI150X4LG	4,0	5/32	150	5,9	100	30	35,0	1,2

ca. 80° Shore A

• Empf. Vorspannung 1 - 2 %

• Zugspannung ca. 13 daN/cm²

Reibwerte μ : Stahl: ca. 0,70 | PE: ca. 0,40 | HDPE: ca. 0,35 | **FDA/EC/BfR-konform**