



PU 85 A transparent glatt

ca. 88° Shore A

• Empf. Vorspannung 1 - 2 %

• Zugspannung ca. 18 daN/cm²

| Artikel Nr. | Profildicke | | max. Profilbreite | | Gebindegröße | | Empfohlener Mind.-Scheiben-Ø | |
|--------------|-------------|------|-------------------|------|--------------|----|------------------------------|------|
| | mm | inch | mm | inch | ft | m | mm | inch |
| FBFK150X1TG | 1,0 | 3/64 | 150 | 5,9 | 100 | 30 | 15,0 | 0,5 |
| FBFK150X16TG | 1,6 | 1/16 | 150 | 5,9 | 100 | 30 | 20,0 | 0,6 |
| FBFK150X2TG | 2,0 | 5/64 | 150 | 5,9 | 100 | 30 | 30,0 | 1,2 |
| FBFK150X3TG | 3,0 | 1/8 | 150 | 5,9 | 100 | 30 | 35,0 | 1,4 |
| FBFK150X4TG | 4,0 | 5/32 | 150 | 5,9 | 100 | 30 | 45,0 | 1,8 |

Reibwerte μ : Stahl: ca. 0,60 | PE: ca. 0,30 | HDPE: ca. 0,25 | **FDA/EC/BfR-konform**