



PU 75 A sky blue smooth Hollow round belts



approx. 80° Shore A

- Recommended pretension:
weldable 6 - 8 %
Fitting connector max. 4 - 6 %
- Working tension
approx. 12 daN/cm²

Diameter Ø inch		Cross section	Weight	Standard Roll		Min. Pulley Ø		Working Load/ Belt*	
Ext. Ø	In. Ø	cm ²	kg/100 m	m	ft	mm	inch	daN/Belt	lbs
3/16	9/128	0.147	1.8	200	656	30	1.2	1.8	3.9
1/4	13/128	0.261	3.2	100	328	45	1.8	3.1	6.9
5/16	17/128	0.420	5.1	100	328	55	2.2	5.0	11.1
3/8	19/128	0.600	7.2	100	328	65	2.6	7.2	15.8
1/2	13/64	1.020	12.4	50	164	85	3.4	12.2	26.9
19/32	13/64	1.560	19	50	164	100	4.0	18.7	41.2

* = coefficient
of friction μ :1

Coefficient of Friction μ

- Steel approx. 0.70
- PE approx. 0.40
- HDPE approx. 0.35

FDA/EC/BfR- conform