

Top side: Transversal grooves (TGA)





Quality: PU65A / PU80A Order No.: FBFJG750X38A

GENERAL BELT INFORMATION					
Material type	Polyurethane	Belt design	monolithic, 2 components		
Total belt thickness	3.8 mm	Weight	2,8 kg/m²		
Minimum pulley diameter	28 mm	Temperature	-20°C+60°C		
Recommended pretension	2%	Maximum production width	700 mm		
Pull force at 1% elongation (static)	0,49 N/mm	Chemical resistance	upon request		
Pull force at 1% elongation (relaxed)	0,34 N/mm				

BELT SPECIFICATIONS	TOP SIDE	BOTTOM SIDE
Approx. material hardness (Shore)	72° Shore A	84° Shore A
Coefficient of friction $\boldsymbol{\mu}$ Steel	n/a	0.6
Color	ultramarine blue	ultramarine blue
Belt thickness	1.6 mm	2,2 mm
Surface	Transversal grooves (TGA)	AT5
Characteristics	FDA (Food and Drug Administration)	FDA (Food and Drug Administration)
	Hydrolysis resistance	MicroClean
	microbial resistant	2C
	MicroClean	
	2C	

CONFORMITY	RECOMMENDED END CONNECTION & WELDING			
REACH EC 1907/2006 in the current versions	PARAMETERS			
EC 1935/2004 in the current versions	Finger joint		Butt welding (heating sword)	
EC 10/2011 in the current versions	Heating plate temperature	n/a °C	Heating paddle temperature	260°C ±10°C
FDA (Food and Drug Administration)	Pressure	n/a bar		
	Heating time	n/a sek.		

The above information is the result of in-house quality testing. It does not constitute a warranty of properties and, in particular, does not contain statements about the suitability of the product for specific purposes, nor can any claims be derived from it against us. The information does not release the buyer, in particular, from his obligation to perform incoming inspection.

Subject to change without notice - 09/2025



MATERIAL CHARACTERISTICS

BEHAbelt conveyor belts additionally offer very useful special features that make them suitable for even the most demanding conveyor belt applications.



FDA/EC compliance for direct food contact.



Metal and X-ray detectable conveyor belts for maximum food safety. These products are part of the PUsafe series.



Hydrolysis-resistant conveyor belts for use in warm, humid, and wet environments.



Specially protected against UV-C radiation.



Use of raw materials of non-animal origin.



Friction driven conveyor belts for roller drives.



Antistatic dissipative conveyor belts with excellent mechanical properties.



The microbe-resistant conveyor belts do not provide a breeding ground for microorganisms.



Unique surface finish that offers optimal release properties and excellent cleanability due to its rounded structure.



The two-component production allows the combination of different material hardnesses, properties, and colors.



Heavy-duty flame retardant according to ISO 340.



Form-locking conveyor belts for gear drives.

DELIVERY PROGRAM

Supplementary product solutions as well as welding and joining technology.



made of PU and TPE



Monolithic conveyor belts Weldable belts made of PU Welding/joining technology for PU and TPE and TPE



PU coatings for toothed and V-belts



Belt accessories made of PU