

Hollow Round Belts

PU85A sapphire blue smooth



approx. 88° Shore A (±3)

Recommended Pretension 4...8%

Coeff. of friction μ steel approx. 0,6

Coeff. of friction μ PE approx. 0,35

Coeff. of friction μ HDPE approx. 0,3

FDA/EC compliant

Article no.	Diameter \varnothing		approx. weight kg/100m	Standard roll		Recommended min. pulley \varnothing		DRIVE Fmax/belt	TRANSPORT max. conveying weight	
	mm	inch		m	ft	mm	inch	Standard N	Standard kg	Standard lbs
FBHK048LG	4,8	3/16	1,8	200	656	35	1,4	29	5,7	12,6
FBHK063LG	6,3	1/4	3,2	100	328	55	2,2	48	9,7	21,3
FBHK080LG	8	5/16	5,1	100	328	65	2,6	78	15,5	34,2
FBHK095LG	9,5	3/8	7,2	100	328	75	3	110	21,9	48,3
FBHK125LG	12,5	1/2	12,4	50	164	100	3,9	187	37,3	82,3
FBHK150LG	15	19/32	19	50	164	120	4,7	286	57,2	126,1

Characteristics



FDA (Food and Drug Administration)

FDA/EC conformity for direct food contact



Vegan

Use of raw materials from non-animal origin



Hydrolysis resistance

Hydrolysis resistance (HY). Suitable for humid environments.



microbial resistant

Microbial resistant materials do not provide a breeding ground for microorganisms.



Cold-flexible

Particularly flexible at low temperatures down to -30°C

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 06/2026