


Round belts

TPE63D silver smooth, Reinforced Polyester



Article no.	Diameter ø		approx. weight	Standard roll		Recommended min. pulley Øø		DRIVE Fmax/belt		TRANSPORT max. conveying weight			
								Standard Overlap		Standard		Overlap	
	mm	inch	kg/100m	m	ft	mm	inch	N	N	kg	lbs	kg	lbs
FBRT095IGA	9,5	3/8	8,5	152	500	190	7,5	284	961	56,7	125,0	192,2	423,7
FBRT125IGA	12,5	1/2	14,8	152	500	270	10,6	491	1272	98,2	216,4	254,4	560,8

approx. 63D / 100A

Max. Preload	
Standard	2 %
Overlap	3 %
Coeff. of friction μ steel approx.	0,3
Coeff. of friction μ PE approx.	0,15
Coeff. of friction μ HDPE approx.	0,1
FDA/EC compliant	

Characteristics



FDA (Food and Drug Administration)





Use of raw materials from non-animal origin



UV resistant Particularly good UV



with reinforcement for applications that require a higher pull force.

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 12/2025