


## Special profiles

### TPE55D blue smooth



| Article no.  | Dimensions | approx.<br>weight | Standard<br>roll |     | Recommended<br>min. pulley Ø |      | DRIVE<br>Fmax/belt | TRANSPORT<br>max. convey-<br>ing weight |                 |
|--------------|------------|-------------------|------------------|-----|------------------------------|------|--------------------|---|-----------------|
|              | mm         | kg/100m           | m                | ft  | mm                           | inch | Standard<br>N      | Standard<br>kg                          | Standard<br>lbs |
| FBKBLP17113W | 16.35x11.3 | 18                | 50               | 164 | 175                          | 7    | 715                | 143,0                                   | 315,3           |
| FBKBLP1711W2 | 16.35x11.3 | 18                | 100              | 328 | 175                          | 7    | 715                | 143,0                                   | 315,3           |

approx. 55D / 100A

Recommended Pretension 2...4%

Coeff. of friction  $\mu$  steel approx. 0,35

Coeff. of friction  $\mu$  PE approx. 0,2

Coeff. of friction  $\mu$  HDPE approx. 0,15

FDA/EC compliant

#### Characteristics



**FDA (Food and  
Drug  
Administration)**

FDA/EC conformity for direct  
food contact

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 12/2025