


T-Profiles

PU65A ultramarine blue smooth



Article no.	Dimensions	approx. weight	Standard roll		Recommended min. pulley Ø		DRIVE Fmax/belt	TRANSPORT max. con- veying weight	
	mm		m	ft	mm	inch	Standard N	Standard kg	Standard lbs
FBTG95X35LA	9.5x3.5	2,4	70	230	20	0,8			

approx. 72° Shore A (±3)

Recommended Pretension 4...8%

Coeff. of friction μ steel approx. 0,8

Coeff. of friction μ PE approx. 0,5

Coeff. of friction μ HDPE approx. 0,45

FDA/EC compliant

Characteristics



Hydrolysis resistance

Hydrolysis resistance (HY).
Suitable for humid environments.



microbial resistant

Microbial resistant materials
do not provide a breeding
ground for microorganisms.



Cold-flexible

Particularly flexible at low
temperatures down to -30°C



FDA (Food and Drug Administration)

FDA/EC conformity for direct
food contact

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 01/2026