

**Quality:** PU70A
**Order No.:** FBKH8X32TG
**Color:** transparent

FDA
EC

| GENERAL PROFILE INFORMATION | | | |
|---|---|---|---|
| Profile Category | Guides and Profiles | k1% relaxed (standard) | 2,8 N \| 0,6 lbf |
| Profile Design | n/a | k1% static (standard) | 3,5 N \| 0,8 lbf |
| Processing Type | n/a | Temperature Range | -20°...+60°C |
| Recommended min. pulley | 25 mm | Standard roll | 150 m |
| Recommended pretension | 4...8% | Chemical Resistance | upon request |

| SPECIFICATIONS | PROFILE | COATING |
|---|---|---|
| Type of Material | Polyurethane | n/a |
| Approx. material hardness (Shore) | 76° Shore A | n/a |
| Color | transparent | n/a |
| Dimensions | 8x3.2 mm | n/a |
| Surface | smooth | n/a |
| Approx. coefficients of friction µ | Steel: 0,75 \| PE: 0,4 \| HDPE: 0,35 | n/a |
| Features | FDA/EC | n/a |
| n/a | n/a | n/a |
| n/a | n/a | n/a |
| n/a | n/a | n/a |
| n/a | n/a | n/a |
| n/a | n/a | n/a |

| CONFORMITY |
|---|
| REACH EC 1907/2006 in the current versions |
| EC 1935/2004 in the current versions |
| EC 10/2011 in the current versions |
| FDA (Food and Drug Administration) |

The above information is based on the results of our internal quality control. It does not constitute a guarantee of any properties and, in particular, does not contain any statements regarding the product's suitability for specific purposes; therefore, no claims against us may be derived from this information. In particular, this information does not relieve the buyer of the obligation to inspect the goods upon receipt.

Subject to change without notice - 2026-11-25 01:56